

AMERCOAT® 90 S

DESCRIPTION

High-performance modified phenolic epoxy (90 Series)

PRINCIPAL CHARACTERISTICS

- High solids tank lining
- Excellent chemical resistance
- Suitable for cycling and long term continuous immersion service.
- Withstands continuous immersion in water up to 60°C (140°F)
- Recommended under thermal insulation on carbon steel or stainless steel up to 200°C (390°F)

Note: Contact your PPG representative for specific chemical resistance information

COLOR AND GLOSS LEVEL

- White, pearl gray
- Flat

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.5 lb/US gal)
Volume solids	58 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 286.0 g/kg UK PG 6/23(92) Appendix 3: max. 348.0 g/l (approx. 2.9 lb/US gal)
Recommended dry film thickness	150 µm (6.0 mils) per coat
Theoretical spreading rate	3.9 m ² /l for 150 µm (155 ft ² /US gal for 6.0 mils)
Dry to handle	16 hours
Overcoating Interval	Minimum: 24 hours Maximum: 12 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



AMERCOAT® 90 S

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Steel

- Abrasive blast cleaning is recommended with a surface profile of 40 – 70 µm (1.6 – 2.8 mils).
- Immersion: blast to Sa 3, ISO 8501-1 or SSPC SP-5.
- Remove all rust, dirt, moisture, grease or other contaminants from the surface

Note: Apply primer as soon as possible after surface preparation to prevent any contamination.

Concrete

- Dried for at least 28 days in good ventilation conditions
 - Moisture content should not exceed 4.5%
 - Concrete must be sound, dry, free from laitance and any contamination
 - Rough surface; eventually abraded by power tool or diamond abrading tool
-

Substrate temperature and application conditions

- Surface temperature during application should be between 10°C (50°F) and 50°C (122°F)
 - Surface temperature during application should be at least 3°C (5°F) above dew point
 - Ambient temperature during application and curing should be between 10°C (50°F) and 43°C (109°F)
-

SYSTEM SPECIFICATION

- For use under thermal insulation do not exceed 200 microns (8 mils) dry film thickness
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 66.7:33.3 (2:1)

- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container
 - Add hardener to base and continue stirring until homogeneous
 - The thinner should be added after mixing the two components
 - Adding too much thinner results in reduced sag resistance and slower cure
-

Induction time

None

Pot life

4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

AMERCOAT® 90 S

Repair

- Spot blast or power tool clean bare substrate to the requirements shown under surface preparation.
- Feather edges of intact coating.
- Remove dust, dirt and contamination before recoating.

Material temperature

Material temperature during application should be between 10°C (50°F) and 40°C (104°F)

Air spray

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.8 – 2.0 mm (approx. 0.070 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Note: A moisture and oil trap in the main air supply is essential

Airless spray

- 28:1 pump or larger

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 5%

Nozzle orifice

Approx. 0.43 – 0.53 mm (0.017 – 0.021 in)

Nozzle pressure

15.0 - 18.0 MPa (approx. 150 - 180 bar; 2176 - 2611 p.s.i.)

Brush/roller

- Only for touch-up and spot repair

Recommended thinner

THINNER 21-06

AMERCOAT® 90 S

Cleaning solvent

THINNER 90-58

Note: All application equipment must be cleaned immediately after use

ADDITIONAL DATA

Overcoating interval for DFT up to 150 µm (6.0 mils)

Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	48 hours	24 hours	16 hours
	Maximum	15 days	12 days	10 days

Note: Surfaces must be clean, dry and free of contamination, immediately prior to recoating.

Curing time for DFT up to 150 µm (6.0 mils)

Substrate temperature	Dry to handle	Service- water immersion
10°C (50°F)	32 hours	14 days
20°C (68°F)	16 hours	7 days
30°C (86°F)	10 hours	4 days

Notes:

- Adequate ventilation must be maintained during application and curing
- Drying times are dependent on air and steel temperature, applied film thickness, ventilation and other environmental conditions

Pot life (at application viscosity)

Mixed product temperature	Pot life
20°C (68°F)	4 hours
30°C (86°F)	2 hours

Note: Since the pot life is limited and shortened by high temperatures, do not mix more material that will be used within the pot life period

SAFETY PRECAUTIONS

- Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods
- Adequate ventilation to remove solvent must be maintained during application and curing

AMERCOAT® 90 S

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



**PPG Protective &
Marine Coatings**

Bringing innovation to the surface.™