

AMERLOCK® 2 GF / SIGMASHIELD™ 2

DESCRIPTION

Two-component, high solids glass flake reinforced polyamine cured epoxy coating

PRINCIPAL CHARACTERISTICS

- Low-temperature curing down to 0°C (32°F)
- Excellent abrasion and impact resistance
- High glass flake level
- Excellent resistance to corrosion
- Long-term protection at areas subject to heavy wear and tear
- Very low water permeability, due to glass flake barrier
- Tar free
- Resistant to splash and spillage of a wide range of chemicals
- Suitable for immersion service
- Compatible with cathodic protection systems
- Up to 750 µm (30.0 mils) DFT in a single coat

COLOR AND GLOSS LEVEL

- Standard and custom colors
- Eggshell

BASIC DATA AT 10°C (50°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.5 lb/US gal)
Volume solids	87 ± 3%
VOC (Supplied)	EPA Method 24: 172.0 g/ltr (1.4 lb/USgal)
Temperature resistance (Continuous)	To 218°C (420°F)
Temperature resistance (Intermittent)	To 232°C (450°F)
Recommended dry film thickness	200 - 750 µm (8.0 - 30.0 mils) depending on system
Theoretical spreading rate	4.4 m ² /l for 200 µm (174 ft ² /US gal for 8.0 mils)
Overcoating Interval	Minimum: 16 hours Maximum: 3 months
Full cure after	16 days

AMERLOCK® 2 GF / SIGMASHIELD™ 2

Data for mixed product

Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry
-------------------	--

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- Intermittent temperature resistance should be less than 5% of the time, and maximum 24 hours
- Temperature resistance is in atmospheric condition. Please contact your PPG representative for immersion condition.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 50 – 100 µm (2.0 – 4.0 mils)
- Suitable primer must be dry and free from any contamination

Substrate temperature

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 50:50 (1:1)

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Very good mechanical mixing of base and hardener is essential
- Thinner should be added after mixing the components
- Filters should be removed from spray equipment

Induction time

None

Pot life

1 hour at 20°C (68°F)

AMERLOCK® 2 GF / SIGMASHIELD™ 2

Air spray

Recommended thinner

THINNER 21-06

Volume of thinner

6 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.5 – 2.0 mm (approx. 0.060 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 5%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 – 0.79 mm (0.021 – 0.031 in)

Nozzle pressure

19.0 - 22.5 MPa (approx. 190 - 225 bar; 2756 - 3264 p.s.i.)

Brush/roller

- Only for touch-up and spot repair
- Due to thixotropy, it is difficult to obtain a smooth film by brush, although this does not affect performance

Cleaning solvent

THINNER 90-58

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
200 µm (8.0 mils)	4.4 m ² /l (174 ft ² /US gal)
750 µm (30.0 mils)	1.2 m ² /l (47 ft ² /US gal)

AMERLOCK® 2 GF / SIGMASHIELD™ 2

Overcoating interval for DFT up to 300 µm (12.0 mils)				
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	16 hours	7 hours	4 hours
	Maximum	1 month	1 month	1 month
Two-component polyurethane coatings	Minimum	16 hours	7 hours	4 hours
	Maximum	14 days	7 days	4 days

Notes:

- Surface should be dry and free from any contamination
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- An extended recoatable window may be allowable in some circumstances, please contact your PPG representative for more details

Curing time for DFT up to 300 µm (12.0 mils)		
Substrate temperature	Dry to handle	Full cure
10°C (50°F)	24 hours	16 days
20°C (68°F)	8 hours	8 days
30°C (86°F)	5 hours	5 days

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1422 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	2 hours
20°C (68°F)	1 hour
30°C (86°F)	30 minutes

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

AMERLOCK® 2 GF / SIGMASHIELD™ 2

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



**PPG Protective &
Marine Coatings**

Bringing innovation to the surface.™